

KAUFMAN

PRODUCT
INFORMATION

KAUFMAN
PRODUCTS
INC.

3811 CURTIS
AVENUE

BALTIMORE,
MARYLAND
21226-1131
www.kaufmanproducts.net

410-354-8600
800-637-6372

Duracrete II VOFT

Description

Duracrete II VOFT is a single-component, fiber-reinforced, rapid setting, vertical/overhead, cement based repair mortar for concrete. It consists of portland cement, lightweight aggregates, air entraining admixture, corrosion inhibitors and proprietary modifiers. When mixed with water, Duracrete II VOFT forms an extremely workable quick setting mortar that possesses high strengths with excellent adhesion and low permeability against carbon dioxide and chloride intrusion. The coefficient of thermal expansion is similar to concrete. The unique feature of Duracrete II VOFT is the tremendous resistance to freeze-thaw cycling and deicing chemicals such as calcium chloride and rock salt, which translates to a more permanent repair of concrete. Additionally, while Duracrete II VOFT is rapid setting, it also is user-friendly due to a working time of 20-30 minutes, making it easy to mix and apply the entire unit before it takes an initial set.

Uses

Duracrete II VOFT is recommended for vertical and overhead concrete repairs of both interior and exterior surfaces, however it may also be used in horizontal applications if desired. Use for patching scaled and spalled concrete as well as resurfacing damaged and honeycombed surfaces. It is ideal for use on parking structures, bridges, retaining walls, ceilings, sloped surfaces, or anywhere concrete surfaces need repair, and especially areas that will be exposed to deicing chemicals. Use from 1/4" to 2" thick overhead and from 1/4" to 3-4" thick on vertical surfaces. Duracrete II VOFT may also be layered for deeper repairs.

Packaging /Yield

50 lb. bag, yielding .45 ft³

50 lb. pail, yielding .45 ft³

Specification

ASTM C-928, Rapid Hardening (R2) *

Directions

Surface Preparation

The concrete substrate must be structurally sound, as well as clean and free of all contaminants and deleterious materials, such as grease, oil, form release agent, curing compounds, laitance, etc. The surface must be prepared to a minimum of a Concrete Surface Profile (CSP) of five, as per ICRI Guideline Number 03732. All oxidation must be removed

from any exposed reinforcing steel. Additionally, once prepared properly, the concrete surface must be saturated surface dry (SSD), unless using an epoxy bonding agent. For proper priming of the steel, use SurePoxy HM, SurePoxy HM Class B, or SurePoxy HMEPL.

Physical Properties - @ 75°F

Vicat Set Times (ASTM C-191/AASHTO T-131)

Initial, 25 mm 18-20 mins.

Final, 25 mm 20-30 mins.

| | | |
|--------------------------------------|---------|-------|
| Compressive Strength (ASTM C-109) | 3 Hours | 3,000 |
| | 1 Day | 4,500 |
| | 7 Days | 6,500 |
| | 28 Days | 7,500 |

| | | |
|---|--------|-------|
| Slant Shear Bond Strength (ASTM C-882) | 1 Day | 1,500 |
| | 7 Days | 2,200 |

| | | |
|--|---------|-----|
| Bond Strength by Direct Tension (ASTM C-1583) | 28 Days | 350 |
|--|---------|-----|

| | | |
|----------------------------------|---------|-----|
| Tensile Strength (ASTM C-496) | 28 Days | 675 |
|----------------------------------|---------|-----|

| | | |
|-----------------------------------|---------|-------|
| Flexural Strength (ASTM C-348) | 1 Day | 500 |
| | 7 Days | 1,200 |
| | 28 Days | 1,400 |

| | |
|-----------------------------------|-----------------|
| Length Change-Wet (ASTM C-157) | +0.06 @ 14 Days |
| | +0.07 @ 28 Days |
| Length Change-Dry (ASTM C-157) | -0.04 @ 14 Days |
| | -0.04 @ 28 Days |

| | |
|---|--------------------------|
| Scaling Resistance (ASTM C-672, 50 cycles) | .68 lbs./ft ² |
|---|--------------------------|

| | |
|---|--------------|
| Chloride Ion Permeability (ASTM C-1202, 360 minutes) | 367 coulombs |
|---|--------------|

| | |
|---|-------|
| Freeze-Thaw Resistance | |
| Relative Dynamic Modulus (ASTM C-666, Procedure A) | 97.6% |

| | |
|---------------------------------------|-------------|
| Surface Resistivity (AASHTO T-358) | 102.0 kΩ-cm |
|---------------------------------------|-------------|

| | |
|--|-----------------------|
| Modulus of Elasticity at 28 Days (ASTM C-469) | 3.2 x 10 ⁶ |
|--|-----------------------|

| | |
|--|------|
| Moisture Content @ 4 Hrs. (ASTM F-2659) | 3.8% |
|--|------|

Mixing

Pour approximately 2.88 quarts of clean water into a mixing container and then slowly add the dry powder. Mix mechanically with a 1/2" drill and mixing paddle for single bag mixes, or a mortar mixer for 3-5 minutes or until uniform. Do not ever add plasticizers, accelerators, retarders, or any other ingredients besides potable water, unless advised in writing by Kaufman Products.

K A U F M A N

PRODUCT
INFORMATION

KAUFMAN
PRODUCTS
INC.

3811 CURTIS
AVENUE

BALTIMORE,
MARYLAND
21226-1131
www.kaufmanproducts.net

410-354-8600
800-637-6372

Application

Duracrete II VOFT must be scrubbed into the substrate, filling all pores and voids, to achieve the proper bond. Force material against edge of repair, working toward center, making certain to compact the material well especially around any exposed reinforcing bars. After filling repair, consolidate, then screed. Material may be applied in multiple lifts or at least ¼." When using multiple lifts in either vertical or overhead applications, be sure to score the top surface of each lift to produce a roughened surface for the next lift. Allow preceding lift to reach final set before placing fresh material. Each lift should be roughened and re-primed with a slurry coat. For structural bond strength, use SurePoxy HM or SurePoxy HMEPL.

The temperature of the mix as well as the ambient temperatures of the area to be repaired will affect the working and set times of Duracrete II VOFT. If using when temperatures are greater than 85°F, we recommend the use of chilled water and cooling the bags in an enclosed environment. During cold weather, (below 40°F) heat the area to be patched until warm to the touch. Also heat Duracrete II VOFT and use at least 80°F water or tent the area to retain heat during the initial set. Curing blankets may also help.

Curing

As per ACI recommendations for portland cement concrete, curing is beneficial. Duracrete II VOFT should be either moist cured with wet burlap, polyethylene, a fine mist of water, or a water-based compatible curing compound such as Krystal 15 Emulsion, Krystal 25 Emulsion, Krystal 30 Emulsion, or a Thinfil Series product.

Do not apply subsequent lifts to a surface to which curing compound was applied. Protect freshly placed Duracrete II VOFT from the effects of sunlight, wind, rain, sleet, and snow.

Notes

Duracrete II VOFT meets all aspects of ASTM C-928, Rapid Hardening (R2) when used at 70 ±15 degrees Fahrenheit. However, Duracrete II VOFT is acceptable for use from 45 degrees Fahrenheit and rising.

Shelf Life

12 months from manufacture date, when stored unopened under recommended conditions. Store between 40 and 85°F and at low humidity. Keep containers tightly closed.

Precautions

Not recommended for use less than 1/4" thick. Do not feather-edge. Temperatures during application should be at least 45°F. Substrate should be damp during application. Read the complete *Safety Data Sheet* and *Concrete Substrate Preparation data sheet* before using.

Technical Information

Test results were achieved under laboratory conditions. Statistical variations will occur based upon mixing methods, temperature & humidity, test methodology, site conditions, curing conditions, application methods, and equipment.

For professional use only. Not for sale or use by the public.

LIMITED WARRANTY: We warrant our products to be of good quality and will replace material proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement, there are no warranties which extend beyond the description on the face hereof, and Kaufman Products, Inc. makes no warranty or guarantee, expressed or implied, including warranties of fitness or merchantability, respecting its products, and Kaufman Products, Inc. shall have no other liability with respect hereto. The user shall determine the suitability of the product or the intended use and assume all risks and liability in connection thereto. Our salespeople, distributors, and their salespeople have no authority to change the printed recommendations concerning the use of our products.