

K A U F M A N

PRODUCT
INFORMATION

KAUFMAN
PRODUCTS
INC.

3811 CURTIS
AVENUE

BALTIMORE,
MARYLAND
21226-1131

410-354-8600
800-637-6372
www.kaufman
products.net

SurePoxy 116

Description

SurePoxy 116 is a 100%-solids, high-modulus, two-component, very fast-setting epoxy gel. SurePoxy 116 provides a rigid, non-shrinking adhesive grout for use in both dry and damp applications. It is insensitive to moisture before, during, and after cure. SurePoxy 116's unique non-abrasive formula makes application significantly easier with pressure injection equipment. SurePoxy 116 is intended for application in temperatures from 33°F to 95°F. Changes in temperature will speed up or slow the strength gain. SurePoxy 116 is especially modified for both rapid set and strength gains.

Uses

Recommended for grouting of anchor bolts, bridge railings, dowel bars (either plain or epoxy coated) in transverse, longitudinal and vertical joints in highway and bridge application, and to seat base plates and heavy vibrating machinery, subject to both high stress and impact. Use to adhere parking bumpers and sealing cracks and ports for injection of epoxy into concrete. SurePoxy 116 is also recommended for testing the adhesion of epoxy systems to concrete using a pipe cap tensile test. SurePoxy 116 is chemically engineered expressly for use with automated injection equipment. Follow pressure equipment manufacturer's directions. Due to its' rapid set time, SurePoxy 116 is also ideal for sealing cracks, and around ports, prior to injection of low viscosity resins.

Specifications

ASTM C-881, Types I, II, IV & V, Grade 3, Classes B & C (modified for faster set)
AASHTO M-235, Types I, II, IV & V, Grade 3, Classes B & C (modified for faster set)

VOC

0 grams/liter

Physical Properties - ¼# Uncured

Mixing Ratio	1:1 by volume
Color	A-white; B-gray; Mixed-gray
Viscosity	Non-Sag Gel
Shelf Life	2-year minimum

Pot Life (conditioned & cured at following temps)

	75°F	42°F
1 quart	5-6 min.	10-20 min.
¼" Bead	10 min.	25-30 min.
Final Cure	1 day	3 days

Cured

HDT (ASTM D-648)	125°F
Bond Strength (ASTM C-882)	2,100 psi. min. @ 14 days
Compressive Strength 1:1 Mortar (ASTM D-695)	4,500 psi. @ 2 hrs 10,500 psi. @ 1 day 12,500 psi. @ 3 days
Compressive Yield Strength	12,000 psi. @ 7 days
Compressive modulus	460,000 psi. @ 7 days
Flexural Strength	15,000 psi. @ 7 days
Shear Strength (ASTM D-732)	3,900 psi. @ 7 days
Water Absorption.5% max (ASTM D-570)	.1%
Pull Out Test (ASTM E-488)	34,000 psi. @ 7 days
Shore D Hardness (ASTM-2240)	80 min.
Shrinkage (ASTM C-883)	.002 max.

All values approximate-will vary with temperature and humidity.

Packaging

22 oz. cartridge (6 per case)
2 gallon unit
10 gallon unit

Temperature Conditions

Store dry at 40-95°F. Condition SurePoxy 116 to at least 70°F before using. If this is not possible, be sure it is at least conditioned to 40°F. ; be aware that it will develop strengths slower.

Directions

Surface Preparation

All surfaces must be free of foreign matter and be structurally sound. Prepare surfaces by acid etching, mechanical scarification or sand-blasting. Drill hole and blow out loose dust and debris from hole using oil and moisture-free compressed air and brush. Remove foreign matter from surfaces.

Application

Static Mixers - Insert the tip of the static mixer all the way to the back of the hole to be grouted. Dispense material and gradually withdraw the mixer as the hole fills up. You can stop pumping SurePoxy 116 into the hole when they are approximately 50% full, as the bar will displace most of the SurePoxy. Check constantly to avoid air pockets and unevenly mixed components.

Hand mixing - Mix until color is completely uniform. Insert into hole and fill from the back outward until the hole is 50% full. Insert anchor or rebar with a twisting motion all the way to the back of the already grouted hole. Attach grout containing plastic disc onto dowel or rebar to prevent run out. For cold weather work it helps to make the discharge opening of static mixers larger by cutting off the smallest opening. Depth of embedment is typically 10-15 times the bolt diameter.

Notes

Clean equipment with aromatic solvents such as Xylene immediately after use. Jobsite tests should be conducted in order to verify anchor performance before using.

Precautions

Store at 40-90° F. Do not thin. Not for sealing cracks under hydrostatic pressure. *Read Safety Data Sheet before using.* This product is intended as an anchoring adhesive in relatively low mass volumes. Please refer to the *General Epoxy Instructions* for complete details on proper application during cold and hot weather.

When used as a vertical/overhead anchoring adhesive that will carry a sustained tension load, this product is intended only for short-term use. This product is manufactured to meet all aspects of ASTM C-881 which includes no performance standards with regard to creep and/or deformation. It is the responsibility of the engineer and/or contractor to determine the suitability of this product for the intended use.

Technical Information

Test results were achieved under laboratory conditions. Statistical variations will occur based upon mixing methods, temperature & humidity, test methodology, site conditions, curing conditions, application methods, and equipment.

For professional use only. Not for sale to or use by the general public.

LIMITED WARRANTY We warrant our products to be of good quality and will replace material proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement, Kaufman Products, Inc makes no warranty or guarantee, expressed or implied, including warranties of fitness or merchantability, respecting its products, and Kaufman Products, Inc shall have no other liability with respect hereto. User shall determine the suitability of the product or the intended use and assume all risks and liability in connection thereto. Our salespeople, distributors and their salespeople have no authority to change the printed recommendations concerning the use of our products.